



TEST REPORT

Colorbiotics

Larry Oien

Date: May, 31th 2011

Report #: 11210 CAN R rev A

Samples #: CushionFall Sport™

Sujet: UV Testing according to FIFA Test Method 10.

Product Tested	
Rubber (CAN000326)	CushionFall Sport

Pick up samples conditions
Received at the laboratory, 10/02/2011.

Test Program	
Test	Standard
Tests (laboratory)	Artificial weathering – EN 14836 Colour Change – EN ISO 20105-A02

This report contains 3 pages. It may not be used for commercial purposes, unless it is reproduced in its entirety. The results are valid only for the complete system as described in this report.


Labosport Inc.
5661, rue de Lanaudière, suite 200
Montréal (Québec) H2G 3A5 - CANADA
Ph: 514 277 9111 / Fax: 514 277 9112
www.labosport.ca

LABOSPORT

Tests Results

EN 14836 - Synthetic surfaces for outdoor sports areas - Exposure to artificial weathering

Sample conditioning:
 - Sample conditioned to **20°C / 50 % R.H.**
 - Sample tested: 30/05/2011
 - Scale graduations: 1 – 1/2 - 2 – 2/3 – 3* – 3/4* - 4* – 4/5* - 5*
 -*FIFA Requirements
 - Operator : M.Benetti

Samples	Properties	Results	FIFA Requirements	Picture Before/After	Pass/Fail
CB 292-36 CushionFall Sport™ (CAN000326)	Colour change	4/5	≥ Grey scale 3		Pass

This report contains 3 pages. It may not be used for commercial purposes, unless it is reproduced in its entirety. The results are valid only for the complete system as described in this report.

Labosport Inc.
 5661, rue de Lanaudière, suite 200
 Montréal (Québec) H2G 3A5 - CANADA
 Ph: 514 277 9111 / Fax: 514 277 9112
www.labosport.ca

LABOSPORT



.....
Guillaume Loubersac
Managing Director
Labosport Inc.

(guillaume.loubersac@labosport.ca)



.....
Mickaël Benetti, T.P.
Laboratory and Site Technician
Labosport Inc.

(mickael.benetti@labosport.ca)

This report contains 3 pages. It may not be used for commercial purposes, unless it is reproduced in its entirety. The results are valid only for the complete system as described in this report.

Labosport Inc.
5661, rue de Lanaudière, suite 200
Montréal (Québec) H2G 3A5 - CANADA
Ph: 514 277 9111 / Fax: 514 277 9112
www.labosport.ca